



مشخصات فنی پوشش کابل ضد آتش

Vardin® FR401

Test	TestMethod	Test Condition	Result	Unit
MFI	ASTM D1238	190°C , 2160g	<1.7	g/10min
Density	ASTM D792	-	1.2	g/cm ³
FireRetardent properties	ASTM D2863	-	32	%
FireRetardent	UL94	-	V0	-